# BRIDGE FIELD POLYMER SDN. BHD.

OFFICE: 49-2, USJ 10/1G, TAIPAN CREST, 47620 SUBANG JAYA, SELANGOR, MALAYSIA FACTORY ADD: No. 172, HALA PERUSAHAAN MENGLEMBU 1, 30200 IPOH, PERAK

> TEL: +60356338444 FAX: +603 56345333 E-Mail: info@bridgefields.com / asmibudin@gmail.com

## Producers of quality polymers

### **SPECIFICATION**

**BRAND NAME** : GRENVIRO – NRG HG (OFF GRADE)

**TYPE** : NATURAL GUM RUBBER

**PRODUCER** : BRIDGE FIELDS RESOURCES S/B

### COMPOUNDING FORMULATON

MATERIALS	PHR
NRG HG	100
ZnO	4
Stearic Acid	2.5
Sulphur	1
CBS	1
TMTD	0.1

# Grenyiro,

### **PACKING STANDARD:**

Each Bale weights : 25 Kgs No of Bale/Pallet : 50 Bales : 1250 Kgs Each crate weighs

Each bale is wrapped in LDPE bags

FLC 20'Container (with 16 Wood Pallet): 20,000 Kgs FLC 20'Container (with OUT Pallet) : 25,000 Kgs

### **FULL CONTAINER LOAD:**

# PHYSICAL PROPERTIES

TENSILE STRENGTH (Mpa)	$18.6 \pm 3$
ELONGATION (E.B) %	$930 \pm 60$
SPECIFIC GRAVITY %	$0.98 \pm 0.2$
RUBBER HYDROCARBON %	95 ± 5
ASH CONTENT %	5 ± 3
ACETONE EXTRACT %	4 ± 1.5
SHORE HARDNESS IRHD	45 ± 15

### \*Specifications are provided without prejudice



### STORAGE:

Store in dry and closed rooms far from heating equipments an at places below 30°C. Protect product against direct sunlight. In these conditions the product can be stored up to 8 months.

with its product literature and upon the request of its customers. BFR provides product specifications and evaluations, suggested formulations and recommendations and other technical assistance, both orally and in writing (collectively the "Technical Information"). In Information to the three und correct, it makes no warranty, either express or implied, as to the accuracy, completeness, or filterations of the Technical Information Literature, in the results which may be obtained by any person using the Technical Information LFR will not be loss or damage, in tort, contract or otherwise, arising from customer's use of BFR products or Technical Information. It is the customer's sole responsibility to test the products and any Technical Information provided to determine whether they are suitable for the customer must read and become familiar with available information concerning its hazards, proper uses, goal en admalling, including all health, safety, and hygiene precautions recommended by the manufacturer. Nothing in the Technical Information is intended to use any product, method, or process in violation of any intellectual property rights governing such product, method, or process. In any such product, method, or process in violation of any intellectual property rights governing such product, method, or process. BFR CORPORATION DISCLAIMS ANY AND ALL WAS AND IMPLED, INCLUDING WITHOUT LIMITATION, WARRANTIES OF MERCHANTABULTY AND PRATICULAR PURPOSO R TECHNICAL INFORMATION PROVIDED BY BY INFORMATION PROVIDED BY